

MAXCIS 362-H

Hybrid Polyurea Based, Waterproofing and Coating Material

DEFINITION:

- It is a two component, solvent free, UV resistant polyurea system.
- It provides excellent mechanical, chemical and corrosion resistance on the applied surface.

USAGE AREAS:

- General waterproofing applications
- Applications under ceramics, screed concrete and other flooring
- On thermal insulation materials
- Foundations



COMPONENTS:

- A Components: MDI Prepolymer - MAXCIS ISO-15
- B Components: Amine Blend - MAXCIS 362-H

FEATURES OF COMPONENTS:

Test Name	Unit	A Component - MAXCIS ISO-15	B Component - MAXCIS 362-H
Chemical Structure	-	MDI Prepolymer	Amine Blend
Density (25°C)	g/cm ³	1,11 ± 0,03	1,02 ± 0,03
Viscosity (25°C)	mPa.s	700 - 800	300-500
Solid Content	%	100	100

APPLICATION CONDITIONS:

For primer and polyurea application;

- The surface must be solid and of sufficient strength.
- You should wait at least 28 days before applying on new concrete.
- The surface temperature must be at least 3 °C higher than the dew point.
- Recommended air and application surface temperature is between 5°C and 35°C.
- Relative humidity should be lower than 85% during application.
- Application should not be made in windy weather.

SURFACE PREPARATION:

- The application surface must be clean and dry. There should be no rust, dust, oil and water.
- Weak layer and mortar residues on the concrete surface should be cleaned by surface grinding method.
- Concrete repairs should be made with suitable epoxy or cement based materials.
- Dilatation and chamfers must be prepared with suitable materials.
- Priming is done with an epoxy or polyurethane based primer suitable for the structure of the surface.

MIXING RATIO OF COMPONENTS:

	By Weight	By Volume
A Component - MAXCIS ISO-15	112 units	100 units
B Component- MAXCIS 362-H	100 units	100 units

REACTION PARAMETERS:

Test Name	Unit	Value
Gel Time	sec.	7-10
Tack Free Time	sec.	20-30

APPLICATION:

- Before application, Component B should be mixed with a low speed mixer for 30 minutes.
- In order for the machine to mix at the correct ratio (100/100 by volume), the gun and machine must be cleaned and maintained before application.
- Machine and hose temperature is adjusted between 65°C and 75°C depending on the surface and air temperature.
- Machine pressure is adjusted between 140-180 bar.
- Application is made perpendicular to the surface and generally in a single layer.
- The color of the applied product changes under direct sunlight. Aliphatic topcoat should be applied to prevent color change.

FINISHED PRODUCT FEATURES:

Test Name	Unit	Method	Value
Tensile Strength	Mpa	ASTM D 638	≥ 14
Elongation	%	ASTM D 638	≥ 300
Shore A	-	ASTM D 2240	85-90
Shore D	-	ASTM D 2240	35-40
Tear Resistance	N/mm	ASTM D 624	≥ 25
Abrasion Resistance	mg	EN ISO 5470-1	< 240 (H22, 1000 cycle)
Impact Resistance	-	EN ISO 6272-1	Class III
Adhesion Strength	N/mm ²	ASTM D 4541	Concrete: ≥ 3 Metal: ≥ 6

CONSUMPTION:

- Consumption for 1 mm thickness is 1.10 kg/m².

PACKAGING:

- Component A 220 kg/barrel, Component B 200 kg/barrel. Total 420 kg/set

SHELF LIFE AND STORAGE:

MAXCIS ISO-15 and MAXCIS 362-H are sensitive to humidity and temperature. Therefore, they should be stored in original, unopened and undamaged packages, in dry environments away from direct sunlight.

	Unit	A Component - MAXCIS ISO-15	B Component - MAXCIS 362-H
Shelf Life	ay	9	9
Storage Temperature	°C	15-25	15-25

WARNING:

- Before using the product, read the MSDS form carefully and follow the written instructions.
- Personal protective equipment should be used during application.
- There must be sufficient air circulation in the application area.
- Give empty packages to organizations authorized to collect hazardous waste.